



EcoVantage Kraft Pro

Benefits

- About 80% kraft and up to 20% recycled fibre
- Mix of renewable resources for the highest performance and recyclable value
- High strength and printability
- Natural look and feel
- Food approval by ISEGA

End-uses

- Food/non-food packaging
- Grocery bags for packed foods for
 - Specialist shops
 - Wholefood markets
 - Organic supermarkets



PEFC	FSC*	BRCGS	Quality Management System	Environmental Management System	Safety Management System
•	•	Packaging and Packaging materials	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

*on demand

Technical Values									
Properties		Method	Typical values						
Basis Weight	g/m ²		70	80	90	100	110	115	120
Burst strength	kPa	ISO 2758	291	369	437	504	582	617	652
Tensile strength MD	kN/m	ISO 1924-3	7,7	8,8	9,9	12	13,8	14,4	15
Tensile strength CD	kN/m	ISO 1924-3	3	3,4	3,9	4,3	4,7	4,9	5,2
TEA MD	J/m ²	ISO 1924-3	64	94	105	117	129	135	140
TEA CD	J/m ²	ISO 1924-3	119	144	162	180	198	207	216
Tear strength MD	mN	ISO 1974	651	744	837	930	1023	1070	1116
Tear strength CD	mN	ISO 1974	721	824	927	1030	1133	1185	1236
Gurley	s	ISO 5636-5	50						
Cobb ₆₀	g/m ²	ISO 535	30						
Moisture	%	ISO 287	7,8						

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.



Issued from 01.01.2021
latest version available on
www.mondigroup.com

Test conditions:
ISO 187:1990
(23 C + 1 C/RH 50% +2)