



Advantage MF Wrap

Benefits

- 100% virgin softwood kraft fibre
- World class strength

End-uses

- Reel wrapping
- Pallet wrapping
- Carrier bags



| PEFC | FSC | Quality Management System | Environmental Management System | Food Safety Regulations |
|------|-----|---------------------------|---------------------------------|-------------------------|
| • | • | ISO 9001:2015 | ISO 14001:2015 | BfR, FDA, CONEG |

Technical Values

| Properties | | Method | | Typical values | | | | |
|---------------------------------|------------------|------------|----------|----------------|------------|--------------|--------------|--------------|
| | | | | | | | | |
| Basis Weight | g/m ² | ISO 536 | | 70 | 80 | 90 | 100 | 110 |
| Thickness | µm | ISO 534 | | 110 | 120 | 135 | 150 | 160 |
| Tensile strength | kN/m | ISO 1924-3 | MD CD | 8,1 4,6 | 9,1 5,2 | 10,7 5,7 | 12,2 6,1 | 13,8 6,3 |
| Stretch | % | ISO 1924-3 | MD CD | 2,5 7,0 | 2,5 6,5 | 2,5 6,5 | 2,5 6,5 | 2,5 6,5 |
| Tear strength | mN | ISO 1974 | MD CD | 750 750 | 900 900 | 1000 1100 | 1200 1350 | 1350 1600 |
| Burst strength | kPa | ISO 2758 | | 390 | 450 | 530 | 590 | 690 |
| Cobb ₆₀ | g/m ² | ISO 535 | | 28 | 28 | 28 | 28 | 28 |
| Pick resistance | CWSN | TAPPI 459 | | 19 | 19 | 19 | 19 | 19 |
| Short-span compressive strength | kN/m | ISO 9895 | CD | - | - | - | 2,2 | 2,5 |



Issued from 01.01.2020,
latest version available on
www.mondigroup.com

Test conditions:
ISO 187:1990
(23 ± 1°C / RH 50 ± 2%)