



Advantage MG White Cote RB

Benefits

- Mixture of softwood and hardwood fibre
- Well-closed formation
- Very high gloss
- Very low porosity
- Suitable for coating and lamination
- Extraordinary silicone holdout
- Great printability

End-uses

- Release base (i.e. labels)
- Sugar sticks
- Envelopes
- Functional paper base



PEFC	FSC*	BRCGS	Quality Management System	Environmental Management System	Safety Management System
•	•	Packaging and Packaging materials	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

*on demand

Technical Values							
Properties		Method		Typical values			
Basis Weight	g/m ²	ISO 536		41	45	47	55
Thickness	µm	ISO 534		45	48	51	54
Tensile strength	kN/m	ISO 1924-3	MD CD	4,0 2,0	4,5 2,4	4,7 2,6	4,9 2,8
Tear strength	mN	ISO 1974	MD CD	190 205	220 240	240 260	260 280
Bendtsen porosity	ml/min	ISO 5636-3		5	5	5	5
Oil absorbency	g/m ²	Scan-P 37.77		2	2	2	2
Moisture	%	On-line		5	5	5	5

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.

MD = Machine Direction CD = Cross Direction

	SPECIALITYWORLD by mondi	Issued from 01.01.2021, latest version available on www.mondigroup.com	Test conditions: ISO 187:1990 (23 C + 1 C/RH 50% +2)
--	------------------------------------	--	---