

Kraft



## ProVantage KraftTop Liner X TYPICAL VALUES

Parameter	Test method	Unit of measure	Substance (g/m <sup>2</sup> )								
			100	110	125*	135*	160*	170*	180*	200	225
Moisture	ISO 287	%	7.8								
Bursting strength	ISO 2758	kPa	341	404	415	452	488	567	583	662	683
SCT <sub>CD</sub>	ISO 9895	kN/m	1.8	2.0	2.2	2.5	2.8	3.2	3.3	3.6	3.9
Tensile Stiffness Index <sub>MD</sub>		kNm/g	11								
Tensile Stiffness Index <sub>CD</sub>		kNm/g	4.8								
Cobb <sub>60</sub> (top)	ISO 535	g/m <sup>2</sup>	30								
Dennison test	TAPPI 459 om-08	No.	16								

\*ECO Premium Service, fast delivery option

Typical values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Valid until: 31.12.2019 or until further notice

IN TOUCH EVERY DAY

[www.mondigroup.com](http://www.mondigroup.com)

### Certificates

- ISEGA
- ISO 9001
- ISO 14001
- OHSAS 18001
- FSC® or PEFC
- EN 13432

Technical Customer Service

**Mondi Świecie S.A.**

Bydgoska 1

86-100 Świecie, Poland

Tel: +48 52 332 1123