



ProVantage KraftTop Liner

Benefits

- Excellent strength
- Burst index: 4.0
- Optimum runnability and processing properties
- Cost efficient
- Ideal alternative to Kraftliner

End-uses

- **Food & beverage packaging:** Fruit & vegetable packaging, Agricultural produce
- **Industrial packaging:** Automotive industry
- **Heavy-duty packaging**



| ISEGA | ISO 9001 | ISO 14001 | OHSAS 18001 | FSC® | PEFC™ |
|-------|----------|-----------|-------------|------|-------|
| • | • | • | • | • | • |

Typical Values*

| Properties | Method | Unit of measure | Substance (lb/1000 ft ²) | | | | | | | | | | |
|--------------------------|----------|---------------------|--------------------------------------|------|------|------|------|------|------|------|------|------|------|
| | | | 20.5 | 22.5 | 23.6 | 24.6 | 25.6 | 27.7 | 28.7 | 30.7 | 32.8 | 34.8 | 35.8 |
| Moisture | ISO 287 | % | 7,8 | | | | | | | | | | |
| Bursting strength | ISO 2758 | lbf/in ² | 59.5 | 66.0 | 68.2 | 70.3 | 72.5 | 76.9 | 79.0 | 82.7 | 86.3 | 88.5 | 91.4 |
| SCT _{CD} | ISO 9895 | lbf/inch | 10.3 | 11.4 | 12.0 | 12.6 | 13.1 | 13.7 | 14.3 | 15.1 | 16.0 | 16.6 | 17.1 |
| Cobb ₆₀ (top) | ISO 535 | g/m ² | 30 | | | | | | | | | | |



Issued from 01.01.2020,
latest version available on
www.mondigroup.com

Test conditions:
Typical values after conditioning, measured
at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

* computed based on SI units