

## **Advantage Protect White**

## **Benefits**

- High Tensile Energy Absorption (TEA)
- Excellent runnability
- High wet Tensile Strength
- Very good printability
- Protection against rain and splash water for 6 hours according EN ISO 2875

## **End-uses**

We particularly recommend its use as an outer layer for pasted valve bags for powdery fillers such as cement, building materials, chemicals, when high protection against moisture is required.



| Management Systems / Certifications                                   |                                  | Food Contact Approvals   |  |
|---|----------------------------------|--|--|
| ISO 9001:2015<br>ISO 14001:2015,<br>ISO 45001:2018,<br>EN 15593:2008; | PEFC-CoC,<br>FSC-CoC,<br>FSC-CW; | German BfR Recommendation XXXVI<br>Code of Federal Regulations, Food and Drugs (FDA), 21 CFR Ch.I (1. April 2019)<br>Source Reduction Council of CONEG |  |

| Properties                      |         | Method     |          | Typical values (please select the 2-10 most common grammages) |              |              |
|---------------------------------|---------|------------|----------|---|--------------|--------------|
| Basis Weight                    | g/m²    | ISO 536    |          | 70  | 80           | 90           |
| Tensile strength                | kN/m    | ISO 1924-3 | md<br>cd | 5.4<br>3.8  | 6.2<br>4.3   | 6.9<br>4.9   |
| Tensile Index                   | Nm/g    | ISO 1924-3 | md<br>cd | 77<br>54  | 77<br>54     | 77<br>54     |
| Stretch at break                | %       | ISO 1924-3 | md<br>cd | 5.8<br>8.6  | 5.8<br>8.6   | 5.8<br>8.6   |
| Tensile Energy Absorption (TEA) | J/m²    | ISO 1924-3 | md<br>cd | 180<br>225  | 205<br>255   | 230<br>285   |
| TEA Index                       | J/g     | ISO 1924-3 | md<br>cd | 2.6<br>3.2  | 2.6<br>3.2   | 2.6<br>3.2   |
| TearIndex                       | mN.m²/g | ISO 1974   | md<br>cd | 14.0<br>16.0  | 14.5<br>16.5 | 14.5<br>16.5 |
| Air Resistance (Gurley)         | S       | ISO 5636-5 |          | 19  | 19           | 19           |
| Cobb <sub>60</sub>              | g/m²    | ISO 535    |          | 22  | 22           | 22           |
| Brightness                      | %       | ISO 2470   |          | 83  | 83           | 83           |
| Wet tensile stregth             |         |            |          | 1.6   | 1.8          | 2.0          |

The table above shows typical values for certain basis weights.

The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.



Issued from 01.01.2021, latest version available on www.mondigroup.com Test conditions: ISO 187:1990 (23°C±1 C/RH 50%±2)