

ProVantage Baywhite



Benefits

- 100% virgin kraft fibre for excellent strength
- Superior appearance for high-quality printing
- Bleached hardwood top sheet ensures brilliant printability

End-uses

- Food & beverage packaging
- Frozen products packaging



Food Contact	ISO 9001	ISO 14001	OHSAS 18001	FSC®	GMP/GHP
•	•	•	•	•	•

Typical Values

Properties	Method	Unit of measure	Substance (g/m ²)						
			115	125	135	160	175	200	250
Moisture	On-line	%	8.0						
Calliper	ISO 534	µm	153	166	179	213	230	263	331
Bursting strength	ISO 2758	kPa	545	600	673	793	814	879	1051
SCT _{CD}	ISO 9895	kN/m	2.43	2.62	2.83	3.25	3.51	3.92	4.60
Scott plybond	TAPPI UM-403	J/m ²	406	382	361	353	331	334	346
Cobb ₆₀ (top)	ISO 535	g/m ²	27			26			24
Cobb ₆₀ (bottom)	ISO 535	g/m ²	31			30	31		30
Cobb ₁₈₀₀ (top)	ISO 535	g/m ²	85	87	89	93	90	92	93
Brightness (top)	ISO 2470	%	80	81	80	82		83	86
Bendtsen roughness (top)	ISO 8791-2	ml/min	364	402	424	506	539	700	986



Issued from 01.01.2021,
latest version available on
www.mondigroup.com

Test conditions:
Typical values after conditioning,
measured at 50 ± 2% RH and 23 ± 1°C
(ISO 187:1990)

WWF's Environmental Paper Company Index: Mondi's constant high packaging score increased from 73.7% in 2013 to 85.7% in 2019.