



Advantage MF SpringPack Plus

Benefits

- High stretch allowing extreme strength properties

End-uses

- Wrapping of spring mattresses



PEFC	FSC	Quality Management System	Environmental Management System	Food Safety Regulations
•	•	ISO 9001:2015	ISO 14001:2015	BfR, FDA, CONEG

Technical Values										
Properties		Method		Typical values						
Basis Weight	g/m ²	ISO 536		100	120	125	130	140	150	160
Thickness	µm	ISO 534		140	175	182	190	210	230	245
Tensile strength	kN/m	ISO 1924-3	MD CD	12,5 5	15,1 5,9	15,6 6,25	16,2 6,5	17,2 6,9	18,7 7,5	19,5 8,0
Stretch	%	ISO 1924-3	MD CD	12,5 9,4	12,5 9,4	12,5 9,4	12,5 9,4	12,5 9,4	12,5 9,4	12,5 9,4
TEA	J/m ²	ISO 1924-3	MD CD	680 310	820 370	855 385	890 400	960 430	1020 465	1080 490
Tear strength	mN	ISO 1974	MD CD	1300 2000	1350 2250	1540 2500	1600 2600	1800 2900	1950 3000	2050 3350
Burst strength	kPa	ISO 2758		740	770	800	830	840	880	920
Cobb ₆₀	g/m ²	ISO 535		28	28	28	28	28	28	28



Issued from 01.01.2021,
latest version available on
www.mondigroup.com

Test conditions:
ISO 187:1990
(23 ± 1°C / RH 50 ± 2%)