



Advantage eCom Tape Base

Benefits

- Natural alternative for plastic tapes
- 100% fresh fibre
- High strength
- High density for optimal coating
- Excellent runnability on coating lines

End-uses

- Water-activated tapes
- Gummed paper tapes



PEFC	FSC*	BRCGS	Quality Management System	Environmental Management System	Safety Management System
•	•	Packaging and Packaging materials	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

*on demand

Technical Values								
Properties		Method	Typical values					
Basis Weight	g/m ²	ISO 536	40	50	60	70	80	90
Thickness	µm	ISO 534	61	74	87	96	112	122
Tensile strength MD	kN/m	ISO 1924-3	4,8	6,0	7,2	8,4	9,6	10,8
Tensile strength CD	kN/m	ISO 1924-3	22	27,5	3,3	3,85	4,4	4,95
Tear strength MD	J/m ²	ISO 1924-3	265	380	520	660	800	940
Tear strength CD	J/m ²	ISO 1924-3	375	525	685	860	1035	1215
Cobb ₆₀	g/m ²	ISO 535	25	25	25	25	25	25
Burst strength	kPa	ISO 2758	200	260	325	395	450	490
Stretch MD	%	ISO 1924-3	1,9	1,9	2,0	2,0	2,0	2,1
Density**	Kg/m ³		655	675	689	729	714	737

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.
**Average figures, not specified

Issued from 01.01.2021,
latest version available on
www.mondigroup.com

Test conditions:
ISO 187:1990
(23 C + 1 C/RH 50% +2)