



EcoVantage eCom Mailer

Benefits

- Natural look & feel
- Contains recycled fibres
- Good strength properties
- Good tear-resistance
- High stiffness
- Excellent runnability
- Advanced printability

End-uses

- Mailer bags



PEFC	FSC*	Food Contact Approvals	Quality Management System	Environmental Management System	Safety Management System
•	•	BfR XXXVI	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

*on demand

Technical Values									
Properties		Method	Typical values						
Basis Weight	g/m ²	ISO 536	70	80	90	100	110	115	120
Thickness**	µm	ISO 534	100	110	120	140	160	165	170
Tensile strength MD	kN/m	ISO 1924-3	6,7	8,0	8,0	8,4	8,8	8,9	9,1
Tensile strength CD	kN/m	ISO 1924-3	2,8	3,2	3,6	3,9	4,1	4,1	4,2
Tear strength MD	J/m ²	ISO 1924-3	560	680	765	850	935	978	1020
Tear strength CD	J/m ²	ISO 1924-3	700	840	945	1050	1155	1208	1260
Cobb ₆₀	g/m ²	ISO 535	30	30	30	30	30	30	30
Burst strength	kPa	ISO 2758	270	350	350	362	378	381	391
Roughness Bendtsen TS**	ml/min	ISO 8791-2	500	500	500	500	500	500	500
Stretch MD	%	ISO 1924-3	1,5	1,6	1,7	1,7	1,7	1,7	1,7
Density**	kg/m ³		690	700	705	705	715	720	720

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.
**Average values, not specified

Issued from 01.01.2022, latest version available on www.mondigroup.com	Test conditions: ISO 187:1990 (23 C + 1 C/RH 50% +2)
--	--