



## Advantage eCom Kraft White

### Benefits

- 100% fresh fibre
- High stiffness
- High strength
- Excellent runnability
- Satisfactory printability

### End-uses

- Mailer bags
- eGrocery bags
- eFood bags



PEFC	FSC*	Food Contact Approvals	Quality Management System	Environmental Management System	Safety Management System
•	•	BfR XXXVI FDA Regulation §§ 176.170 FDA Regulation §§ 176.180	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

\*on demand

### Technical Values

Properties		Method	Typical values				
Basis Weight	g/m <sup>2</sup>	ISO 536	70	75	80	90	100
Thickness**	µm	ISO 534	105	110	115	130	145
Tensile strength MD	kN/m	ISO 1924-3	6,3	6,8	7,2	8,1	9,0
Tensile strength CD	kN/m	ISO 1924-3	3,9	4,1	4,4	5,0	5,5
Tear strength MD	J/m <sup>2</sup>	ISO 1924-3	1 127	1 245	1 288	1 440	1 600
Tear strength CD	J/m <sup>2</sup>	ISO 1924-3	1 274	1 433	1 504	1 737	2 020
Cobb <sub>60</sub>	g/m <sup>2</sup>	ISO 535	27	27	27	27	27
Burst strength	kPa	ISO 2758	334	367	382	432	482
Roughness Bendtsen TS**	ml/min	ISO 8791-2	880	930	980	1 070	1 170
Stretch MD	%	ISO 1924-3	2,5	2,5	2,5	2,6	2,7
Brightness	%	ISO 2470	83	83	83	83	83
Density**	kg/m <sup>3</sup>		805	805	805	805	805

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.

\*\*Average values, not specified

Issued from 01.01.2022,  
latest version available on  
[www.mondigroup.com](http://www.mondigroup.com)

Test conditions:  
ISO 187:1990  
(23 C + 1 C/RH 50% +2)