

Advantage eCom Smooth White



Benefits

- High strength
- Excellent printability
- 100% fresh fibre
- Excellent runnability
- High puncture resistance properties

End-uses

- Mailer bags
- Shopping bags
- eGrocery
- eFood delivery bags



PEFC	FSC*	Food Contact Approvals	Quality Management System	Environmental Management System	Safety Management System
•	•	BFR XXXVI FDA Regulation §§ 176.170 FDA Regulation §§ 176.180	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

*on demand

Technical Values									
Properties		Method	Typical values						
Basis Weight	g/m ²	ISO 536	70	75	80	90	100	110	120
Thickness	µm	ISO 534	97	102	109	122	134	146	160
Tensile strength MD	kN/m	ISO 1924-3	7,7	8,3	8,8	9,9	11,0	12,1	13,2
Tensile strength CD	kN/m	ISO 1924-3	3,6	3,9	4,2	4,7	5,2	5,7	6,2
Tear strength MD	mN	ISO 1974	805	900	1000	1170	1300	1485	1680
Tear strength CD	mN	ISO 1974	910	1013	1136	1305	1450	1683	1836
Cobb ₆₀	g/m ²	ISO 535	25	25	25	25	25	25	25
Burst strength	kPa	ISO 2758	300	345	368	414	460	506	552
Brighness	%	ISO 2470	85	85	85	85	85	85	85
Roughness Bendtsen TS	ml/min	ISO 8791-2	220	220	230	250	270	270	270
Stretch MD	%	ISO 1924-3	2,0	2,0	2,0	2,0	2,0	2,0	2,0
Density**	kg/m ³		845	850	850	855	860	865	865

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.
**Average values, not specified

Issued from 01.01.2022, latest version available on www.mondigroup.com	Test conditions: ISO 187:1990 (23 C + 1 C/RH 50% +2)
--	--